

Q/FLEX

Q FLEX IS A SINGLE PACK, QUICK CURING URETHANE JOINT SEALANT THAT GIVES HIGH FLEXIBILITY AND IS RESISTANT TO AGEING

PREPARATION-DIRECTIONS-APPLICATION

Surface must be structurally sound, clean, dry & free of foreign matter. Remove oil, grease, asphalt, tar, paint, rust, wax waterproofing & form release agents.

For friable surfaces or water immersion Q/Seal should be used as a primer.

For best performance, depth of sealant should be one half the joint width. Minimum depth should be 6mm. Cure of sealant is dependent upon absorption of moisture from the atmosphere. Cure progresses faster under conditions of high relative humidity.

To apply, angle out nozzle to appropriate size and puncture inner seal. Remove metal cover from base of cartridge with a screwdriver and fit in cartridge gun.

Fill from bottom joint to prevent air pockets & voids. Sealant may be tooled with shaping tool moistened with water. Wipe off & leave joint concave. Clean equipment immediately after use with Q/Solve.

Available in 310ml Cartridges or 600ml Foils. Barrel gun required for 600ml Foils.



Joint Uses:

Jointing Rubber & EVA Mats Roof & Gutter Expansion Construction Pre Cast Panels Silage Pits Effluent Tanks Slurry Pits

Colour	Black
100% Modulus	0-21 NM
Initial Cure	4-6 Hours
Full Cure	3-7 Days
Elongation At Bre	ak 500%
Packed In	320 & 600 CC
Chemical Resista	nce Good to a wide range of acids, alkalis, salt etc
Coverage	310ml = 9 Linear Metres
per 6mm x 6mm	Joint 600ml = 17.5 Linear Metres
Flash Point	>100C
Vapour Pressure	<u>@</u> 20ද <100 mbar
Specific Gravity @	20c 1.42 g/cm3
Solubility in/Misci	oility Insoluble

USE GLOVES & PROTECTIVE EQUIPMENT. IF SPLASHED IN EYES FLUSH WITH PLENTY OF WATER & SEEK MEDICAL ADVICE. IF INGESTED DO NOT INDUCE VOMITING. SEEK MEDICAL ADVICE.

Equestrian • Agricultural • Gym • Play

Quattro Products Limited, Milestone House Ind Est, Penrith, Cumbria, CA11 9NQ

Tel: 01768864977 Email: enq@quattrorubberandresin.co.uk Web: www.quattrorubberandresin.co.uk

